

APPLICATIONS TEMPERATURES OF LIQUID ASPHALTS & EMULSIONS

*The following values are based on what we feel provides optimal results for spray applications. Missouri Department of Transportation specifications are noted in parenthesis.

Degrees Fahrenheit

<u>CUTBACKS</u>	<u>Minimum</u>	<u>Maximum</u>
MC-30	125 (70)	175 (150)
MC-250	175 (150)	250 (220)
MC-800	200 (180)	275 (260)
MC-3000	225 (210)	300 (290)

<u>Emulsions</u>	<u>Minimum</u>	<u>Maximum</u>
SS1H	125 (120)	160 (160)
CHFRS-2P	150 (130)	180 (180)
CSS1H	125 (120)	160 (160)
CRS2	150 (125)	185 (185)
CRS2-P	150 (130)	180 (180)
EA90/HFE90	150	180
EA90P	150 (130)	180 (180)
EA150/HFE150	150	180
EA300/HFE300	150	180