

CRSP		
Illinois Department of Transportation		
TEST ON EMULSIFIED ASPHALT:	<u>Minimum</u>	<u>Maximum</u>
RESIDUE BY DIST. METHOD %	65	
OIL DISTILLATE, % BY VOLUME		3
VISCOSITY S.F. AT <u>122°</u> F, SECS	100	400
SIEVE TEST <u>20</u> MESH-%	----	0.1
STORAGE STABILITY 24 HOURS		1
PARTICLE CHARGE	Positive	
TEST ON PAVING & INDUSTRIAL ASPHALTS (RESIDUE OF LIQUID EMULSIFIED ASPHALTS)		
PENETRATION AT 77° F	100	200
DUCTILITY AT 77° F-CMS	30	----
ELASTIC RECOVERY %	50	