

CRS-2**Missouri Department of Transportation**

| TEST ON EMULSIFIED ASPHALT: | <u>Minimum</u> | <u>Maximum</u> |
|---|-----------------------|-----------------------|
| RESIDUE BY DIST. METHOD % | 65 | |
| OIL DISTILLATE, % BY VOLUME | | 3 |
| VISCOSITY S.F. AT 122° F, SECS | 100 | 400 |
| DEMULSIBILITY 35ML 80% | 40 | |
| SIEVE TEST 20 MESH % | ---- | 0.1 |
| STORAGE STABILITY 24 HOURS | | 1 |
| PARTICLE CHARGE | | Positive |
| TEST ON PAVING & INDUSTRIAL ASPHALTS (RESIDUE OF LIQUID EMULSIFIED ASPHALTS) | | |
| PENETRATION AT 77° F | 90 | 150 |
| DUCTILITY AT 77° F-CMS | 40 | ---- |
| SOLUBILITY IN TRICHLOROETHYLENE % | 97.5 | |
| ELASTIC RECOVERY % | 50 | |