

**ILLINOIS DEPARTMENT OF TRANSPORTATION SPECIFICATIONS FOR
HIGH FLOAT EMULSIONS**

HFE-90, HFE-150, and HFE-300 are medium setting and shall be according to the following table.

Test	HFE-90	HFE-150	HFE-300
Viscosity, Saybolt Furol, at 122 °F (50 °C), (AASHTO T 59), SFS ¹	50 min.	50 min.	50 min.
Sieve Test, No. 20 (850 μm), retained on sieve, (AASHTO T 59), %	0.10 max.	0.10 max.	0.10 max.
Storage Stability Test, 1 day, (AASHTO T 59), %	1 max.	1 max.	1 max.
Coating Test (All Grades), (AASHTO T 59), 3 minutes	Stone coated thoroughly		
Distillation Test, (AASHTO T 59): Residue from Distillation test to 500 °F (260 °C), % Oil Distillate by volume, %	65 min. 7 max.	65 min. 7 max.	65 min. 7 max.
Characteristics of residue from distillation test to 500 °F (260 °C): Penetration at 77 °F (25 °C), (AASHTO T 49), 100 g, 5 sec, dmm	90-150	150-300	300 min.
Float Test at 140 °F (60 °C), (AASHTO T 50), sec.	1200 min.	1200 min.	1200 min.

¹ The emulsion shall be pumpable