

APPLICATIONS TEMPERATURES OF LIQUID ASPHALTS & EMULSIONS

The following values are based on what we feel provides optimal results for spray applications.

Degrees Fahrenheit

<u>CUTBACKS</u>	<u>Minimum</u>	<u>Maximum</u>
MC-30	125	175
MC-250	150	220
MC-800	180	260
MC-3000	225	290

**Temperatures may be above flash point. Take precautions to prevent fire or explosion.

Degrees Fahrenheit

<u>Emulsions</u>	<u>Minimum</u>	<u>Maximum</u>
SS-1H	120	160
SS-1HP	120	175
CHFRS-2P	130	180
CPEM-1	120	175
CSS-1H	120	160
CSS-1HP	70	160
CRS-2	125	180
CRS-2P	130	180
EA-90/HFE-90	125	180
EA-90P	130	180
EA-150/HFE-150	130	180
EA-300/HFE-300	130	180
NTEA	150	180